


HIPOST™ OPERATING GUIDELINES: SERIES 12J1R, 12L1R & 2J1R



* When ae is less than 25% DC, recommend use of Chip Thinning Calculator to ensure hmax falls within fz range.

ISO	Materials			V _c Cutting Speed SFM	f _z Feed/Tooth (inch)	Harder <-----> Tougher										Coolant
	Mat'l Group #VDI 3323	Type	Examples			PCD	Cermets		Carbide							
							IN0560	IN2504	IN10K	IN2010	IN2540	IN2505	IN2005	IN4030	IN2530	
P	1 thru 5	Non-alloy Steel	1018, A36, 1045, A572, 1070	400-1000	.003-.007					4	2	1	3	NO		
				600-1600		1										
	6 thru 9	Low-alloy Steel	4140, 4340, P20, 8620, 300M	350-700						4	2	1	3			
				500-1000		1										
10, 11	High-alloy Steel	H13, A2, D2, M2, T1	300-600					4	2	1	3					
			400-800	1												
M	12 thru 13	Stainless Steel (Ferritic & Martensitic)	410, 416, 440	350-600	.003-.006										YES May not be required at high speeds	
	14			303, 304, 316, 15-5, 17-4		300-550					3	2	1			
K	15 thru 16	Gray Cast Iron	CLS. 20, 30, 45	500-1000	.003-.007										NO	
	17 thru 20			Nodular Cast Iron		60-40-18, 100-70-03	400-800		2	1	3			4		
N	21 thru 30	Aluminum	7075, 6061	1000-3000	.003-.008	1			1						YES	
S	31 thru 35	High-Temp Alloys	Inconel, Hastelloy, Nimonic, Monel	65-150	.003-.005							2	3	1	YES	
	36 thru 37			Titanium Alloys		6AL-4V, 5Al-5Mo-5V-3Cr	85-200							3		2
H	38 thru 39	Hardened Steel >48	A2, 01, D2	130-250	.003-.004					1			2		NO	

Note: Feed and speed recommendations are starting operating parameters. They are only guidelines from which further optimization should take place. Operating parameters are influenced by many machining variables. These variables may cause for reductions in feeds and speed or dramatic increases. Additionally, DOC and WOC may need to be revised to optimize the tools performance.